



RASACAST A-16M

Type of Product: High Alumina Medium Cement Dense Castable (M.C.C)

Physical Properties:

Raw material basis	Low iron fire clay
Max Service Temperature (°C)	1580
Dry castable required (Kg/m ³)	2250 - 2350
Approximate amount of water required (%)	7.5 - 8.5
Bulk density after drying at 110°C (Kg/m ³)	2300 - 2400
Grain size (mm)	0 - 5

Thermomechanical Properties:

	Cold Crushing Strength (Kg/Cm ²)	Modulus of Rupture (Kg/Cm ²)	Linear Change (%)
After drying at 110 ° C	≥ 500	≥ 60	negligible
After heating at 1400° C	≥ 600	≥ 90	- 0.3 to -0.8

Chemical Analysis (%):

Al ₂ O ₃	SiO ₂	Fe ₂ O ₃	CaO
51 - 56	35 - 40	1.3 - 1.7	3 - 3.5

Packing in 30 Kg Bags.

- All data subject to reasonable deviations, and therefore, should not be used for specification purposes.
- ASTM Test Methods, where applicable, used for determination of data.

Rev. date : 96/03/20