



RASACAST A-18LV

Type of Product: High Alumina Low Cement Dense Castable (L.C.C)

Physical Properties:

Raw material basis	Tabular alumina
Max Service Temperature (°C)	1850
Dry castable required (Kg/m ³)	2900 - 3000
Approximate amount of water required (%)	5.6 - 6
Bulk density after drying at 110°C (Kg/m ³)	2950 - 3050
Grain size (mm)	0 - 5

Thermomechanical Properties:

	Cold Crushing Strength (Kg/Cm ²)	Modulus of Rupture (Kg/Cm ²)	Linear Change (%)
After drying at 110 ° C	≥ 700	≥ 65	Negligible
After heating at 1500° C	≥ 1000	≥ 110	-0.5 to 0.5

Chemical Analysis (%):

Al ₂ O ₃	SiO ₂	Fe ₂ O ₃	CaO
96 - 97	0.5 - 1.2	≤ 0.15	2 - 2.5

Packing in 25 Kg Bags.

- All data subject to reasonable deviations, and therefore, should not be used for specification purposes.
- ASTM Test Methods, where applicable, used for determination of data.

Rev. date : 95/11/28