



RASAMOR C-15

Type of Product: Fire Clay Anneal set Mortar

Physical Properties:

| | |
|---|-----------|
| Raw material basis | Fire clay |
| Approximate amount of water for trowelling consistency (liters/40 Kg) | 12 - 15 |
| Approximate average amount required per standard NF1 brick (gr) | 150 |
| Grain size (mm) | 0 - 0.3 |
| Type of bonding | Ceramic |

Refractoriness test:

Dose not squeeze or flow from joints when heated for 5 hours at 1400 °C

Chemical Analysis (%):

| Al ₂ O ₃ | SiO ₂ | Fe ₂ O ₃ | CaO |
|--------------------------------|------------------|--------------------------------|-----------|
| 38 - 41 | 54 - 57 | 2.5 - 3 | 0.3 - 0.8 |

Application: Insulating bricks (Gr. 18, 23, 24) and fireclay bricks.

Packing in 40 Kg Bags.

- All data subject to reasonable deviations, and therefore, should not be used for specification purposes.
- ASTM Test Methods, where applicable, used for determination of data.

Rev. date : 98/09/20