



## RS.IS.523LI

**Type of Product:** Insulating Fire Brick (Grade : 23 )

### Physical Properties:

Max Service Temperature (°C)	1260
Bulk Density (Kg/m <sup>3</sup> )	500 - 590
Cold Crushing Strength (Kg/Cm <sup>2</sup> )	≥ 9
Modulus of Rupture (Kg/Cm <sup>2</sup> )	≥ 4
Linear shrinkage after reheating at 1180°C for 24 hours (%)	< 2

### Thermal Conductivity (Kcal/m.h.°C):

@ 400 °C	0.17 - 0.19
@ 600 °C	0.19 - 0.21

### Chemical Analysis (%):

Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	Fe <sub>2</sub> O <sub>3</sub>
28 - 32	65 - 68	0.7 - 0.8

- The above data are typical of the properties of commercial standard brick.
- The data are subject to reasonable variations and therefore should not be used for specification purposes.
- ASTM Test Methods, where applicable, used for determination of data.

Rev. date :95/11/21