



## RS.IS.1023

**Type of Product:** Insulating Fire Brick (Grade :23 )

### Physical Properties:

Max Service Temperature (°C)	1260
Bulk Density (Kg/m <sup>3</sup> )	1000 -1100
Cold Crushing Strength (Kg/Cm <sup>2</sup> )	≥ 25
Modulus of Rupture (Kg/Cm <sup>2</sup> )	≥ 10
Linear shrinkage after reheating at 1180°C for 24 hours (%)	< 2

### Thermal Conductivity (Kcal/m.h.°C):

@ 400 °C	0.37 - 0.39
@ 600 °C	0.39 - 0.41

### Chemical Analysis (%):

Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	Fe <sub>2</sub> O <sub>3</sub>
32 - 35	54 - 57	2.5 - 3

- The above data are typical of the properties of commercial standard brick.
- The data are subject to reasonable variations and therefore should not be used for specification purposes.
- ASTM Test Methods, where applicable, used for determination of data.

Rev. date : 96/03/17