



## RS.IS.1024

**Type of Product:** Insulating Fire Brick (Grade : 24)

### Physical Properties:

Max Service Temperature (°C)	1320
Bulk Density (Kg/m <sup>3</sup> )	1000 - 1100
Cold Crushing Strength (Kg/Cm <sup>2</sup> )	≥ 25
Modulus of Rupture (Kg/Cm <sup>2</sup> )	≥ 9
Linear shrinkage after reheating at 1250°C for 24 hours (%)	< 2

### Thermal Conductivity (Kcal/m.h.°C):

@ 400 °C	0.37 - 0.39
@ 600 °C	0.39 - 0.41

### Chemical Analysis (%):

Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	Fe <sub>2</sub> O <sub>3</sub>
43 - 46	51 - 55	1.3 - 1.5

- The above data are typical of the properties of commercial standard brick.
- The data are subject to reasonable variations and therefore should not be used for specification purposes.
- ASTM Test Methods, where applicable, used for determination of data.

Rev. date : 97/01/28