



RS.IS.1028

Type of Product: Insulating Fire Brick (Grade : 28)

Physical Properties:

Max Service Temperature (°C)	1540
Bulk Density (Kg/m ³)	1000 - 1100
Cold Crushing Strength (Kg/Cm ²)	≥ 25
Modulus of Rupture (Kg/Cm ²)	≥ 8
Linear shrinkage after reheating at 1400°C for 24 hours (%)	< 2

Thermal Conductivity (Kcal/m.h.°C):

@ 400 °C	0.40 - 0.42
@ 600 °C	0.42 - 0.44

Chemical Analysis (%):

Al ₂ O ₃	SiO ₂	Fe ₂ O ₃
63 - 66	29 - 32	0.9 - 1

- The above data are typical of the properties of commercial standard brick.
- The data are subject to reasonable variations and therefore should not be used for specification purposes.
- ASTM Test Methods, where applicable, used for determination of data.

Rev. date : 96/03/17