



RASAMOR C-15AS

Type of Product: Fire Clay Airset Mortar

Physical Properties:

Raw material basis	Fire clay
Approximate amount of water for trowelling consistency (liters/40 Kg)	12 - 15
Approximate average amount required per standard NF1 brick (gr)	150
Grain size (mm)	0 - 0.3
Type of bonding	Chemical / Ceramic

Refractoriness test:

Dose not squeeze or flow from joints when heated for 5 hours at 1400 °C

Chemical Analysis (%):

Al ₂ O ₃	SiO ₂	Fe ₂ O ₃	CaO
36 - 40	55 - 58	2.5 - 3	0.3 - 0.8

Application: Insulating bricks (Gr. 18, 23, 24) and fireclay bricks.

Packing in 40 Kg Bags.

- All data subject to reasonable deviations, and therefore, should not be used for specification purposes.
- ASTM Test Methods, where applicable, used for determination of data.

Rev. date : 98/09/20