



RASAGUN A-17

Type of Product: High Alumina Dense Gunning Mix

Physical Properties:

Raw material basis	Bauxite
Max Service Temperature (°C)	1650
Approximate amount of water required	Under Nozzle
Bulk density after drying at 110°C (Kg/m ³)	2500 - 2600
Grain size (mm)	0 - 5

Thermomechanical Properties:

	Cold Crushing Strength (Kg/Cm ²)	Linear Change (%)
After drying at 110 ° C	≥ 450	negligible
After heating at 1400° C	≥ 500	-2 to -2.7

Chemical Analysis (%):

Al ₂ O ₃	SiO ₂	Fe ₂ O ₃	CaO
81 - 84	6 - 8	1.5 - 2	4 - 5

Packing in 30 Kg Bags.

- All data subject to reasonable deviations, and therefore, should not be used for specification purposes.
- ASTM Test Methods, where applicable, used for determination of data.

Rev. date : 96/04/13