



## RASAGUN C-13

**Type of Product:** Fire Clay Gunning Mix

### Physical Properties:

Raw material basis	Fire clay
Max Service Temperature (°C)	1300
Approximate amount of water required	Under Nozzle
Bulk density after drying at 110°C (Kg/m <sup>3</sup> )	2000 - 2100
Grain size (mm)	0 - 5

### Thermomechanical Properties:

	Cold Crushing Strength (Kg/Cm <sup>2</sup> )	Linear Change (%)
After drying at 110 ° C	≥ 250	negligible
After heating at 1200° C	≥ 200	-0.2 to -0.8

### Chemical Analysis (%):

Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	Fe <sub>2</sub> O <sub>3</sub>	CaO
40 - 43	31 - 34	7.5 - 8.5	12 - 15

### Packing in 30 Kg Bags.

- All data subject to reasonable deviations, and therefore, should not be used for specification purposes.
- ASTM Test Methods, where applicable, used for determination of data.

Rev. date : 95/11/27