



## RASAGUN LC-13

**Type of Product :** Fire Clay Light Weight Gunning Mass

### Physical Properties:

Raw material basis	Light weight fire clay
Max Service Temperature (°C)	1300
Dry Mass required (Kg/m <sup>3</sup> )	1400 - 1500
Approximate amount of water required	Under Nozzle
Bulk density after drying at 110°C (Kg/m <sup>3</sup> )	1450 - 1550
Grain size (mm)	0 - 5

### Thermomechanical Properties:

	Cold Crushing Strength (Kg/Cm <sup>2</sup> )	Linear Change (%)
After drying at 110 ° C	≥ 50	negligible
After heating at 1200° C	≥ 35	-0.8 to -0.2

### Chemical Analysis (%):

Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	Fe <sub>2</sub> O <sub>3</sub>	CaO
33 - 36	37 - 40	7 - 8	12 - 14

### Packing in 40 Kg Bags.

- All data subject to reasonable deviations, and therefore, should not be used for specification purposes.
- ASTM Test Methods, where applicable, used for determination of data.

Rev. date : 95/11/27