



RS.IS.618 P

Type of Product: Insulating Fire Brick (Perlite Base) with good thermal shock resistance

Physical Properties:

Max Service Temperature (°C)	900
Bulk Density (Kg/m ³)	600-650
Cold Crushing Strength (Kg/Cm ²)	≥ 10
Linear shrinkage after reheating at 850°C for 24 hours (%)	≤ 1.5

Thermal Conductivity (Kcal/m.h.°C):

@ 400 °C	0.18 - 0.2
@ 600 °C	0.21 - 0.23

Chemical Analysis (%):

Al ₂ O ₃	SiO ₂	Fe ₂ O ₃
28-34	59-65	1-1.6

- The above data are typical of the properties of commercial standard brick.
- The data are subject to reasonable variations and therefore should not be used for specification purposes.
- ASTM Test Methods, where applicable, used for determination of data.

Rev. date : 03/10/26