



RASABLOCK A-16NV

Type of Product: Preshaped block

Physical Properties:

Raw material basis	Low iron fire clay
Max Service Temperature (°C)	1550
Bulk density as used (Kg/m ³)	≥ 2200
Linear shrinkage after reheating at 1200°C for 24 hours (%)	< -0.5
Cold Crushing Strength (Kg/Cm ²)	≥ 500

Chemical Analysis (%):

Al ₂ O ₃	SiO ₂	Fe ₂ O ₃	CaO
40 - 44	51 - 55	1.6 - 2.1	< 0.5

-All data based on cast specimens. ASTM procedure, where applicable used for determination of data.

-All data subject to reasonable deviations, and therefore, should not be used for specification purposes.

Rev. date : 03/09/12