



## RASAMOR C-15AS

**Type of Product:** Fire Clay Airset Mortar

### Physical Properties:

Raw material basis	Fire clay
Approximate amount of water for trowelling consistency (liters/40 Kg)	12 - 15
Approximate average amount required per standard NF1 brick (gr)	150
Grain size (mm)	0 - 0.3
Type of bonding	Chemical/Ceramic

### Refractoriness test:

Dose not squeeze or flow from joints when heated for 5 hours at 1400 °C

### Chemical Analysis (%):

Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	Fe <sub>2</sub> O <sub>3</sub>	CaO
43 - 46	43 - 46	2 - 2.6	0 - 1

**Application :** Insulating bricks (Gr. 18, 23, 24) and fireclay bricks.

### Packing in 40 Kg Bags.

- All data subject to reasonable deviations, and therefore, should not be used for specification purposes.
- ASTM Test Methods, where applicable, used for determination of data.

Rev. date : 03/09/01