



RASACAST A-16B

Type of Product: High Alumina Dense Castable

Physical Properties:

Raw material basis	Low iron fire clay & bauxite
Max Service Temperature (°C)	1600
Dry castable required (Kg/m ³)	2350 - 2450
Approximate amount of water required (%)	7.5 - 8.5
Bulk density after drying at 110°C (Kg/m ³)	2450 - 2550
Grain size (mm)	0 - 5

Thermomechanical Properties:

	Cold Crushing Strength (Kg/Cm ²)	Modulus of Rupture (Kg/Cm ²)	Linear Change (%)
After drying at 110 ° C	≥ 700	≥ 75	negligible
After heating at 1400° C	≥ 800	≥ 80	- 0.8 to -1.5

Chemical Analysis (%):

Al ₂ O ₃	SiO ₂	Fe ₂ O ₃	CaO
67 - 70	22 - 25	1.3 - 1.7	3.8 - 4.3

Packing in 30 Kg Bags.

- All data subject to reasonable deviations, and therefore, should not be used for specification purposes.
- ASTM Test Methods, where applicable, used for determination of data.

Rev. date : 03/08/03