



## RASAMOR A-17

**Type of Product:** High Alumina Anneal set Mortar

### Physical Properties:

Raw material basis	High alumina materials
Approximate amount of water for trowelling consistency (liters/40 Kg)	11 - 13
Approximate average amount required per brick (gr)	150
Type of bonding	Ceramic
Grain size (mm)	0 - 0.3

### Refractoriness test:

Dose not squeeze or flow from joints when heated for 5 hours at 1700 °C

### Chemical Analysis (%):

Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	Fe <sub>2</sub> O <sub>3</sub>
81 - 84	13 - 16	0.4 - 0.7

**Application :** High Alumina bricks up to 92%

**Packing in 30 Kg Bags.**

- All data subject to reasonable deviations, and therefore, should not be used for specification purposes.
- ASTM Test Methods, where applicable, used for determination of data.

Rev. date : 03/09/01